

Series # 654

Material group	Hardness	SFM	Feed Rate - IPR									
			1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	≤100 Bhn	130	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
	>100-260 Bhn	100	•	0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	•
Free-cutting steels	≤24 Rc	130	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
	>24-30 Rc	100	•	0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	•
Unalloyed heat-treatable steels	≤16 Rc	130	•	0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	•
	16-24 Rc	100	•	0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	•
	24-30 Rc	50	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
Alloyed heat-treatable steels	24-30 Rc	65	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Unalloyed case hardened steels	≤230 Bhn	130	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
Alloyed case hardened steels	24-30 Rc	55	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Nitriding steels	≥24-30 Rc	45	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
Tool steels	≤24 Rc	65	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
	>24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
High speed steels	≥14-30 Rc	•	•	•	•	•	•	•	•	•	•	•
Spring steels	≤330 Bhn	•	•	•	•	•	•	•	•	•	•	•
Stainless steels, sulphured austenitic martensitic	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	•	•	•	•	•	•	•	•	•	•	•	•
	•	•	•	•	•	•	•	•	•	•	•	•
Hardened steels	≤40-48 Rc	•	•	•	•	•	•	•	•	•	•	•
	>48-60 Rc	•	•	•	•	•	•	•	•	•	•	•
Special alloys	≤38 Rc	•	•	•	•	•	•	•	•	•	•	•
Cast iron	≤240 Bhn	130	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
	<300 Bhn	100	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
Spheroidal graphite iron and malleable cast iron	≤240 Bhn	115	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
	<300 Bhn	80	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
Chilled cast iron	≤350 Bhn	•	•	•	•	•	•	•	•	•	•	•
Ti and Ti-alloys	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	>24-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Aluminium and Al-alloys	≤120 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al wrought alloys	≤150 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al cast alloys ≤ 10 % Si	≤200 Bhn	260	•	0.0065	0.0100	0.0125	0.0160	0.0160	0.0180	0.0200	0.0245	•
	> 10 % Si	225	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
Magnesium alloys	≤150 Bhn	325	•	0.0050	0.0080	0.0100	0.0125	0.0125	0.0140	0.0160	0.0200	•
Copper, low-alloyed	≤120 Bhn	130	•	0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	•
Brass, short-chipping long-chipping	≤200 Bhn	•	•	•	•	•	•	•	•	•	•	•
	•	160	•	0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	•
Bronze, short-chipping	≤200 Bhn	130	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
	>200-260 Bhn	115	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
Bronze, long-chipping	≤24 Rc	100	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
	>24-30 Rc	80	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
Duroplastics	-	65	•	0.0030	0.0050	0.0065	0.0080	0.0080	0.0090	0.0100	0.0125	•
Thermoplastics	-	100	•	0.0040	0.0065	0.0080	0.0100	0.0100	0.0110	0.0125	0.0160	•
Reinforced plastics - Kevlar	-	•	•	•	•	•	•	•	•	•	•	•
Reinforced plastics - GFK / CFK	-	•	•	•	•	•	•	•	•	•	•	•

Series # 657

Material group	Hardness	SFM	Feed Rate - IPR									
			1/16 in. 1.590 mm	1/8 in. 3.170 mm	1/4 in. 6.350 mm	3/8 in. 9.520 mm	1/2 in. 12.700 mm	5/8 in. 15.870 mm	3/4 in. 19.050 mm	1 in. 25.400 mm	1 1/4 in. 31.750 mm	1 1/2 in. 38.100 mm
Common structural steels	≤100 Bhn	•	•	•	•	•	•	•	•	•	•	•
	>100-260 Bhn	•	•	•	•	•	•	•	•	•	•	•
Free-cutting steels	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	>24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
Unalloyed heat-treatable steels	≤16 Rc	•	•	•	•	•	•	•	•	•	•	•
	16-24 Rc	•	•	•	•	•	•	•	•	•	•	•
	24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
Alloyed heat-treatable steels	24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
	>30-38 Rc	•	•	•	•	•	•	•	•	•	•	•
Unalloyed case hardened steels	≤230 Bhn	•	•	•	•	•	•	•	•	•	•	•
Alloyed case hardened steels	24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
	>30-38 Rc	45	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065	•	•	•	•
Nitriding steels	≥24-30 Rc	•	•	•	•	•	•	•	•	•	•	•
	>30-38 Rc	40	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065	•	•	•	•
Tool steels	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	>24-30 Rc	40	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065	•	•	•	•
High speed steels	≥14-30 Rc	40	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065	•	•	•	•
Spring steels	≤330 Bhn	30	0.0007	0.0020	0.0030	0.0040	0.0050	0.0050	•	•	•	•
Stainless steels, sulphured austenitic martensitic	≤24 Rc	55	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080	•	•	•	•
	•	40	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065	•	•	•	•
	•	45	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065	•	•	•	•
Hardened steels	≤40-48 Rc	10	0.0005	0.0015	0.0025	0.0030	0.0040	0.0040	•	•	•	•
	>48-60 Rc	•	•	•	•	•	•	•	•	•	•	•
Special alloys	≤38 Rc	25	0.0005	0.0015	0.0025	0.0030	0.0040	0.0040	•	•	•	•
Cast iron	≤240 Bhn	•	•	•	•	•	•	•	•	•	•	•
	<300 Bhn	•	•	•	•	•	•	•	•	•	•	•
Spheroidal graphite iron and malleable cast iron	≤240 Bhn	•	•	•	•	•	•	•	•	•	•	•
	<300 Bhn	•	•	•	•	•	•	•	•	•	•	•
Chilled cast iron	≤350 Bhn	30	0.0010	0.0025	0.0040	0.0050	0.0065	0.0065	•	•	•	•
Ti and Ti-alloys	≤24 Rc	40	0.0007	0.0020	0.0030	0.0040	0.0050	0.0050	•	•	•	•
	>24-38 Rc	25	0.0007	0.0020	0.0030	0.0040	0.0050	0.0050	•	•	•	•
Aluminium and Al-alloys	≤120 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al wrought alloys	≤150 Bhn	•	•	•	•	•	•	•	•	•	•	•
Al cast alloys ≤ 10 % Si	≤200 Bhn	•	•	•	•	•	•	•	•	•	•	•
	> 10 % Si	•	•	•	•	•	•	•	•	•	•	•
Magnesium alloys	≤150 Bhn	•	•	•	•	•	•	•	•	•	•	•
Copper, low-alloyed	≤120 Bhn	•	•	•	•	•	•	•	•	•	•	•
Brass, short-chipping long-chipping	≤200 Bhn	•	•	•	•	•	•	•	•	•	•	•
	•	•	•	•	•	•	•	•	•	•	•	•
Bronze, short-chipping	≤200 Bhn	•	•	•	•	•	•	•	•	•	•	•
	>200-260 Bhn	•	•	•	•	•	•	•	•	•	•	•
Bronze, long-chipping	≤24 Rc	•	•	•	•	•	•	•	•	•	•	•
	>24-30 Rc	90	0.0012	0.0030	0.0050	0.0065	0.0080	0.0080	•	•	•	•
Duroplastics	-	•	•	•	•	•	•	•	•	•	•	•
Thermoplastics	-	•	•	•	•	•	•	•	•	•	•	•
Reinforced plastics - Kevlar	-	•	•	•	•	•	•	•	•	•	•	•
Reinforced plastics - GFK / CFK	-	•	•	•	•	•	•	•	•	•	•	•