

Tools with bold feed column no. are preferred choice.

Pilot holes are always necessary for drilling depths over 7 x D:

1. The pilot hole can be produced with a short, rigid drill. The diameter should be 0.01 - 0.02 mm larger than the diameter of the Ratio drill. Drilling depth $\geq 1 \times D$.
2. Alternatively, the Ratio Drills can produce their own pilot hole. Cutting speed and feed rate must therefore be reduced by 30-40%.
3. A coolant pressure of 40 bar is recommended.

For safety reasons it is very important, that a drill does not exceed a speed of $n = 6\ 000$ rev./min when not supported. The centrifugal forces could break these long tools before reaching the workpiece surface!

Drill \varnothing mm	Feed column no.								
	1	2	3	4	5	6	7	8	9
	f (mm/rev.)								
0.50	0.004	0.006	0.007	0.008	0.010	0.012	0.014	0.016	0.019
1.00	0.006	0.008	0.012	0.014	0.016	0.018	0.020	0.023	0.025
2.00	0.020	0.025	0.032	0.040	0.050	0.063	0.080	0.100	0.125
2.50	0.025	0.032	0.040	0.050	0.063	0.080	0.100	0.125	0.160
3.15	0.032	0.040	0.050	0.063	0.080	0.100	0.125	0.160	0.160
4.00	0.040	0.050	0.063	0.080	0.100	0.125	0.160	0.200	0.200
5.00	0.040	0.050	0.063	0.080	0.100	0.125	0.160	0.200	0.250
6.30	0.050	0.063	0.080	0.100	0.125	0.160	0.200	0.250	0.315
8.00	0.063	0.080	0.100	0.125	0.160	0.200	0.250	0.315	0.315
10.00	0.080	0.100	0.125	0.160	0.200	0.250	0.315	0.400	0.400
12.50	0.080	0.100	0.125	0.160	0.200	0.250	0.315	0.400	0.500
16.00	0.100	0.125	0.160	0.200	0.250	0.315	0.400	0.500	0.630
20.00	0.125	0.160	0.200	0.250	0.315	0.400	0.500	0.630	0.630
25.00	0.160	0.200	0.250	0.315	0.400	0.500	0.630	0.800	0.800
31.50	0.160	0.200	0.250	0.315	0.400	0.500	0.630	0.800	1.000
40.00	0.200	0.250	0.315	0.400	0.500	0.630	0.800	1.000	1.250
50.00	0.250	0.310	0.400	0.500	0.630	0.800	1.000	1.250	1.250
63.00	0.315	0.400	0.500	0.630	0.800	1.000	1.250	1.600	1.600
80.00	0.400	0.500	0.630	0.800	1.000	1.250	1.600	1.600	2.000

Cooling:
 without coolant ducts
 with coolant ducts

Coolant:
 Air
 Neat oil
 Soluble oil

Cutting direction:
 right-hand cutting
 left-hand cutting

Material group	Material examples, new description (old description in brackets) <i>Figures in bold = material no. to DIN EN</i>	Tensile str. MPa (N/mm ²)	Hard- ness	Cool- ant
Common structural steels	1.0035 S185(S133), 1.0486 P275N(STE285), 1.0345 P235GH(H1), 1.0425 P265GH(H2) 1.0050 E295 (St50-2), 1.0070 E360 (St70-2), 1.8937 P500NH (WStE500)	≤ 500 >500-850		<input type="checkbox"/>
Free-cutting steels	1.0718 11SMnPb30 (9SMnPb28), 1.0736 11SMn37 (9SMn36) 1.0727 46S20 (45S20), 1.0728 (60S20), 1.0757 46SPb20 (45SPb20)	≤ 850 850-1000		<input type="checkbox"/>
Unalloyed heat-treatable steels	1.0402 C22, 1.1178 C30E (Ck30) 1.0503 C45, 1.1191 C45E (Ck45) 1.0601 C60, 1.1221 C60E (Ck60)	≤ 700 700-850 850-1000		<input type="checkbox"/>
Alloyed heat-treatable steels	1.5131 50MnSi4, 1.7003 38Cr2, 1.7030 28Cr4 1.5710 36NiCr6, 1.7035 41Cr4, 1.7225 42CrMo4	850- ≤ 1000 1000-1200		<input type="checkbox"/>
Unalloyed case hardened steels	1.0301 (C10), 1.1121 C10E (Ck10)	≤ 750		<input type="checkbox"/>
Alloyed case hardened steels	1.7043 38Cr4 1.5752 15NiCr13, 1.7131 16MnCr5, 1.7264 20CrMo5	850- ≤ 1000 1000-1200		<input type="checkbox"/>
Nitriding steels	1.8504 34CrAl6 1.8519 31CrMoV9, 1.8550 34CrAlNi7	≥ 850 - ≤ 1000 >1000-1200		<input type="checkbox"/>
Tool steels	1.1750 Cr7W5, 1.2067 102Cr6, 1.2307 29CrMoV9 1.2080 X210Cr12, 1.2083 X42Cr13, 1.2419 105WCr6, 1.2767 X45NiCrMo4	≤ 850 >850-1000		<input type="checkbox"/>
High speed steels	1.3243 S 6-5-2-5, 1.3343 S 6-5-2, 1.3344 S 6-5-3	≥ 850 -1000		<input type="checkbox"/>
Spring steels	1.5026 55Si7, 1.1716 55Cr3, 1.8159 51CrV4 (51CrV4)		≤ 330 HB	<input type="checkbox"/>
Stainless steels, sulphured austenitic martensitic	1.4005 X12CrS13, 1.4104 X14CrMoS17, 1.4105 X6CrMoS17, 1.4305 X8CrNiS18-9 1.4301 X5CrNi18-10 (V2A), 1.4541 X6CrNiTi18-10, 1.4571 X6CrNiMoTi 17-12-2 (V4A) 1.4057 X20CrNi 7 2 (X17CrNi16-2), 1.4122 X39CrMo17-1, 1.4521 X2CrMoTi18-2	≤ 850 ≤ 850 ≤ 850		<input type="checkbox"/>
Hardened steels	-		≤ 40 -48 HRC >48-60 HRC	<input type="checkbox"/>
Special alloys	Nimonic, Inconel, Monel, Hastelloy	≤ 1200		<input type="checkbox"/>
Cast iron	0.6010 EN-GJL-100(GG10), 0.6020 EN-GJL-200(GG20) 0.6025 EN-GJL-250(GG25), 0.6035 EN-GJL-350(GG35)	≤ 240 HB <300 HB		<input type="checkbox"/>
New cast materials CGI	EN-GJV250 (GGV25), EN-GJV350 (GGV35) EN-GJV400 (GGV40), EN-GJV500 (GGV50), SiMo 6	≤ 220 HB <300 HB		<input type="checkbox"/>
New cast materials ADI	EN-GJS-900-8 (AD1800), EN-GJS-1000-5 (AD1000) EN-GJS-1200-2 (AD1200), EN-GJS-1400-1 (AD1400)	800-1000 1200-1400		<input type="checkbox"/>
Spheroidal graphite iron and malleable cast iron	0.7050 EN-GJS-500-7(GGG50), 0.8035 EN-GJMw-350-4(GTW35) 0.7070 EN-GJS-700-2(GGG70), 0.8170 EN-GJMB-700-2(GTSS70)		≤ 240 HB ≤ 300 HB	<input type="checkbox"/>
Chilled cast iron	-		≤ 350 HB	<input type="checkbox"/>
Ti and Ti-alloys	3.7024 Ti99.5, 3.7114 TiAl5Sn2.5, 3.7124 TiCu2 3.7154 TiAl6Zr5, 3.7165 TiAl6V4, 3.7184 TiAl4Mo4Sn2.5, -TiAl8Mo1V1	≥ 850 >850-1200		<input type="checkbox"/>
Aluminium and Al-alloys	3.0255 Al99.5, 3.2315 AlMgSi1, 3.3515 AlMg1	≤ 400		<input type="checkbox"/>
Al wrought alloys	3.0615 AlMgSiPb, 3.1325 AlCuMg1, 3.3245 AlMg3Si, 3.4365 AlZnMgCu1.5	≤ 450		<input type="checkbox"/>
Al cast alloys $\leq 10\%$ Si > 10% Si	3.2131 G-AlSi5Cu1, 3.2153 G-AlSi7Cu3, 3.2573 G-AlSi9 3.2581 G-AlSi12, 3.2583 G-AlSi12Cu, - G-AlSi12CuNiMg	≤ 600 ≤ 600		<input type="checkbox"/>
Magnesium alloys	3.5200 MgMn2, 3.5812.05 G-MgAl8Zn1, 3.5812.05 G-MgAl6Zn1	≤ 450		<input type="checkbox"/>
Copper, low-alloyed	2.0070 SE-Cu, 2.1020 CuSn6, 2.1096 G-CuSn5ZnPb	≤ 400		<input type="checkbox"/>
Brass, short-chipping long-chipping	2.0380 CuZn39Pb2, 2.0401 CuZn39Pb3, 2.0410 CuZn43Pb2 2.0250 CuZn20, 2.0280 CuZn33, 2.0332 CuZn37Pb0.5	≤ 600 ≤ 600		<input type="checkbox"/>
Bronze, short-chipping	2.1090 CuSn7ZnPb, 2.1170 CuPb5Sn5, 2.1176 CuPb10Sn 2.0790 CuNi18Zn19Pb	≤ 600 >600-850		<input type="checkbox"/>
Bronze, long-chipping	2.0916 CuAl5, 2.0960 CuAl9Mn, 2.1050 CuSn10 2.0980 CuAl11Ni, 2.1247 CuBe2	≤ 850 >850-1000		<input type="checkbox"/>